

### PRODUCT DESCRIPTION

Stonkote HT4 is a two-component, 100% solids, epoxy coating. It is specifically formulated to provide outstanding protection from a wide range of chemicals while increasing abrasion resistance and cleanability. Stonkote HT4 is easily applied and hardens to an attractive gloss finish.

### USES, APPLICATIONS

Stonkote HT4 is an excellent protective coating and enhances the chemical and abrasion resistance of Stonclad flooring systems. Stonkote HT4 also exhibits outstanding cleanability with an attractive appearance.

### PRODUCT ADVANTAGES

- 100% solids
- Long-term abrasion and corrosion resistance
- Excellent bond strength ensures good adhesion
- Protects against moisture penetration
- Easy to apply to vertical and horizontal surfaces
- Durable gloss finish permits easy cleaning and maintenance
- Factory proportioned packaging ensures consistent, high quality mixing

### PACKAGING

Stonkote HT4 is packaged in units for easy handling. Each unit consists of:

- 1 carton containing:
  - 4 foil bags of Part A (curing agent)
  - 4 poly bags of Part B (resin)

### COVERAGE

Approximately 400 sq. ft./37.16 sq. m per unit at 4 to 6 mil thickness over a porous substrate.

### STORAGE CONDITIONS

Store all components of Stonkote HT4 between 60 to 85°F/16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

### COLOUR

Stonkote HT4 is available in 14 standard colours and in a clear gloss finish. Custom colours are available upon request.

### SURFACE PREPARATION

#### *Preparing Stonhard Flooring Systems*

Before coating a Stonhard floor, all trowel marks and surface

### PHYSICAL CHARACTERISTICS

Percent Solids	100%
Pot Life (@ 77°F/25°C)	.25 minutes
Suggested Number of Coats	One - dark colours Two - light colours
Theoretical Coverage @ 4.0 mil (DFT)	400 sq. ft./37.16 sq. m
Cure Rate (@ 77°F/25°C)	.4 to 5 hours for tack-free surface .24 hours minimum for normal operations
Temperature Limitations	.200°F/93°C (continuous exposure) .250°F/121°C (intermittent exposure)
Fire Resistance of Dry Film	Self-extinguishing

**Note:** The above physical properties were measured in accordance with the referenced standards. Samples of the actual coating were used as test specimens.

imperfections must be removed to produce a smooth surface. Grind the floor using a floor grinder with medium stones and vacuum using an industrial wet/dry vacuum to remove all dust particles. The Stonhard floor is now ready to be coated with Stonkote HT4.

#### *Preparing Concrete Substrates*

Proper preparation is critical to ensure an adequate bond. The substrate must be dry and free of all wax, grease, oils, fats, soil, loose or foreign materials and laitance. Laitance and unbonded cement particles must be removed by mechanical methods, i.e., abrasive blasting or scarifying. Other contaminants may be removed by scrubbing with a heavy-duty industrial detergent (Stonkleen DG2) and rinsing with clean water. The surface must show open pores throughout and have a sandpaper texture. For recommendations or additional information regarding substrate preparation, contact Stonhard's Technical Service Department.

### PRIMING

For use over a Stonhard floor, no primer is necessary. For use over a concrete substrate, HT Primer or Stoncrest GS3 is recommended to ensure maximum product performance.

## MIXING

Stonkote HT4 is supplied in factory proportioned quantities. To achieve thorough and proper mixing, Stonkote HT4 must be mechanically mixed using a heavy-duty, slow speed drill (400 to 600 rpm) with a Jiffy Mixer. Pour the contents of Part B into a mixing container and pre-mix to ensure the suspension of solids. Add Part A and continue to mix to a uniform consistency for 1 to 2 minutes. Avoid high-speed mixing that will entrain air into the mix. Thorough mixing of the two components is essential.

## POT LIFE

After mixing, Stonkote HT4 has a working time of approximately 25 minutes at 77°F/25°C. The working time may vary depending upon ambient and surface conditions.

## APPLYING

Stonkote HT4 can be applied at ambient temperatures of 60 to 85°F/16 to 30°C and humidity below 80%. Stonkote HT4 must be applied immediately after mixing the two components. Stonkote HT4 is applied with a rubber squeegee and backrolled with a medium nap roller. The roller is used to remove squeegee lines and smooth out the surface. A brush may be used where necessary. Stonkote HT4 may be applied at a variable thickness ranging from 4 to 6 mil minimum dry film thickness. Each additional coat may be applied when the surface is tack-free, approximately 4 to 5 hours. Any questions regarding the application of Stonkote HT4 should be directed to Stonhard's Technical Service Department.

## CURING

The surface of Stonkote HT4 will be tack-free in 4 to 5 hours at 77°F/25°C. The coated area may be put back in service in 24 hours. Ultimate physical and chemical characteristics will be achieved in 7 days.

## RECOMMENDATIONS

- Apply only on a clean, sound and properly prepared substrate.
- Minimum ambient and surface temperatures are 60°F/16°C at the time of application.
- Do not use water or steam in the vicinity of the application. **Moisture can seriously affect the working time and properties of the material.**
- Application and curing times are dependent upon ambient and surface conditions.

## PRECAUTIONS

- Toluene and Xylene solvents are recommended for clean up of the unreacted Stonkote HT4 material. The reacted material will require mechanical means of removal. Use these materials only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- The use of safety glasses and impervious gloves is required during application.

- In case of contact, flush the area with copious amounts of water for 15 minutes and seek medical attention. Wash skin with soap and water.
- Use only with adequate ventilation.

## NOTES

- For environments not referenced in the Chemical Resistance Guide, consult Stonhard's Technical Service Department for recommendations.
- Material Safety Data Sheets for Stonkote HT4 are available on line at [www.stonhard.com](http://www.stonhard.com) under Tech Info or upon request.
- A staff of technical service engineers is available to assist with product application or to answer questions related to Stonhard products.
- Requests for technical literature or service can be made through local sales representatives and offices, or corporate offices located worldwide.

## CHEMICAL RESISTANCE GUIDE

The purpose of this guide is to aid in determining the potential value of Stonkote HT4 when exposed to the damaging effects of corrosive chemical environments.

## RATING CODE

E - Excellent  
 G - Good  
 NR - Not Recommended  
 OS - Suitable for use where "occasional spillages" occur; when flushing with water immediately follows.

### ACIDS

	RATING
Acetic - 15%	E
Acetic - 50%	OS
Acetic - Glacial	NR
Benzoic - Sat. 3%	E
Boric - Sat. 30%	E
Butyric - 10%	OS
Chromic - 10%	E
Chromic - 15%	E
Chromic - 40%	OS
Citric - 50%	E
Cresylic	OS
Diglycolic	G
Fatty	E
Fluoboric	G
Formic - up to 10%	G
Heptanoic	OS
Hydrochloric - Conc.	E
Hydrofluoric - 15%	E

	RATING
Hypochlorous - 5%	E
Lactic - up to 20%	E
Maleic - 30%	E
Maleic - 40%	G
Nitric - 10%	G
Nitric - 30%	OS
Oleic	G
Oxalic - Sat	E
Perchloric - 35%	G
Phosphoric - up to 50%	G
Picric - Sat	E
Phthalic	G
Succinic - Sat	E
Sulfuric - 20%	E
Sulfuric - 50%	G
Sulfuric - 70%	OS
Tannic - Sat	E
Tartartic - Sat	E

### ALKALIES AND SALTS

Stonkote HT4 is rated *Good* to *Excellent* when exposed to most alkalis and salts.

### SOLVENTS AND OTHER CHEMICALS

	RATING
Acetone	OS
Alcohol (Methyl)	G
Alcohol (Ethyl, Propyl, Isopropyl, Butyl)	G
Benzene	E
Carbon Tetrachloride	E
Corn Oil	E
Cyclohexane	E
Diacetone Alcohol	E
Ethylene Glycol	E
Ether	OS
Formaldehyde	E
Gasoline	E
Glycerine	E
Hydrogen Peroxide - 10%	E
JP5 Jet Fuel	E
Juices - Fruit	E
Juices - Vegetable	E
Lard	G

	RATING
Linseed Oil	E
Methyl Ethyl Ketone	G
Methylene Chloride	NR
Milk	E
Mineral Spirits	E
Naphtha	E
Oils - Cutting	E
Oils - Mineral	E
Oils - Vegetable	G
Perchloroethylene	E
Skydrol	G
Sucrose (Sugar) - Sat	E
Toluene	E
Trichloroethylene	G
Urea	E
Vinegar (Household)	E
Water	E
Xylene	E

**Note:** This data is based on laboratory tests performed under carefully controlled conditions. (All solutions are at ambient temperatures, 72°F/22°C) No warranty can be expressed or implied regarding the accuracy of this information as it applies to actual plant operations or job site use. Plant operations and job site uses vary widely and the individual results obtained are affected by the specific conditions encountered, which are beyond our control.

**IMPORTANT:**

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

10/08  
Rev. 05/09



**STONHARD**  
[www.stonhard.ca](http://www.stonhard.ca)

An **RPM** Company

**Worldwide Offices:**

Canada 800.263.3112  
USA 800.257.7953

Mexico (52)55.9140.4500  
South America (54-3327)44.2222

Europe (32)2.720.8982  
Middle East (971)4.3470460

Africa (27)11.254.5500  
Asia (86)21.5466.5118