

PRODUCT DESCRIPTION

Stonseal GS7 is a two-component, high performance, waterborne, polyurethane coating. Stonseal GS7 combines superior chemical and abrasion resistance with excellent adhesion and resistance to ultraviolet light.

USES, APPLICATIONS

Stonseal GS7 is a general service urethane coating designed to improve cleanability, increase stain resistance and abrasion resistance, and improve UV resistance. It may be applied to vertical and horizontal surfaces. Typical uses for GS7 include:

- UV resistant topcoat
- Increased abrasion resistance
- Increased stain resistance

PRODUCT ADVANTAGES

- Maximum ultraviolet light resistance
- Easily cleaned surface for simple maintenance
- Excellent abrasion resistance
- Minimal odour during application
- May be applied with a brush or a roller

PACKAGING

Stonseal GS7 is packaged in units for easy handling. Each unit consists of:

- One carton containing:
 - 1 foil bag of Part A (curing agent)
 - 1 gallon pail of Part B (resin)

COVERAGE

Approximately 400 sq. ft./37.16 sq. m per unit per coat @ 2 mil (DFT) over a smooth substrate. GS7 clear flat requires two coats for a proper finish.

STORAGE CONDITIONS

Store both components of Stonseal GS7 between 60 to 85°F/16 to 30°C in a dry area. Avoid excessive heat. Do not freeze. The shelf life is one year in the original, unopened container.

COLOUR

Stonseal GS7 is currently available in a clear gloss, a clear flat and 15 dynamic colours. Custom colours are available upon request.

SURFACE PREPARATION

Before coating a Stonhard floor, the surface must be clean and dry. If applying Stonseal GS7 over an epoxy coating, it is important to

PHYSICAL CHARACTERISTICS

Pot Life	1 hour
(@ 77°F/25°C)	
VOC Content	2.1 lbs./gal
Cure Rate	6 hours
(@77°F/25°C)	for tack-free surface
	24 hours minimum
	for normal operations
Fire Resistance of Dry Film	Self-extinguishing
Abrasion Resistance	0.03 gm weight loss
(ASTM D-4060, CS-17 wheel)	

allow the epoxy to cure for at least 12 hours at 77°F/25°C. The surface must be clean and free of dust and bond inhibiting particles. The Stonhard floor is then ready to be coated.

MIXING

Stonseal GS7 is supplied in pre-measured quantities. Mixing must be achieved by mechanical means. Mechanical mixing should be done using a heavy-duty, slow-speed drill (400 to 600 rpm) with a Jiffy Mixer. Pre-mix Part B in its container to assure the suspension of solids. While the mixing blade is turning, slowly add the Part A and continue to mix to a uniform consistency for one minute. Avoid high-speed mixing that will entrain air bubbles. Thorough mixing of the two components is necessary.

POT LIFE

After mixing, Stonseal GS7 has a working time of one hour at 77°F/25°C.

APPLYING

Stonseal GS7 must be applied at ambient temperatures of 60 to 85°F/16 to 30°C and humidity below 80%. Application should begin immediately after mixing the two components. Use a medium nap roller and apply at a wet film thickness of 3 to 4 mil. Any questions regarding the application of Stonseal GS7 should be directed to Stonhard's Technical Service Department.

CURING

The curing time of Stonseal GS7 is 6 hours at 77°F/25°C. Before resuming normal operations, a curing period of 48 hours is recommended. The coating will achieve ultimate physical characteristics in 7 days.

RECOMMENDATIONS

- Apply only on a clean, sound, properly prepared substrate.
- Application and curing times are dependent upon ambient and surface conditions.
- Minimum ambient and surface temperature is 60°F/16°C at the time of application.

PRECAUTIONS

- Water is recommended for clean up of Stonseal GS7 material spills. The cured material will require mechanical means of removal.
- NIOSH/MSHA approved respirators, safety goggles and impervious gloves are recommended.
- In case of contact with eyes, flush with water for 15 minutes and seek medical attention. Wash skin with soap and water.
- Mechanical ventilation is recommended.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonblend Cleaning Procedures.
- Specific information regarding chemical resistance is available in the Stonblend Chemical Resistance Guide.
- Material Safety Data Sheets for Stonseal GS7 are available upon request.
- A staff of technical service engineers is available to assist with product application, or to answer questions related to Stonhard products.
- Requests for technical literature or service can be made through local sales representatives and offices, or corporate offices located worldwide.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

11/07
Rev. 05/09



STONHARD
www.stonhard.ca

An RPM Company

Worldwide Offices:

Canada 800.263.3112
USA 800.257.7953

Mexico (52)55.9140.4500
South America (54-3327)44.2222

Europe (32)2.720.8982
Middle East (971)4.3470460

Africa (27)11.254.5500
Asia (86)21.5466.5118