

# PRODUCT DATA



## FLUID EPOXY High Performance Fluid Epoxy

### PRODUCT DESCRIPTION

Five Star Fluid Epoxy is a two component, all-purpose, rapid cure fluid epoxy system. Five Star Fluid Epoxy is designed for adhesive grouting, anchoring, anchor bolts, setting of bolts and wedges, and small repairs to concrete.

### ADVANTAGES

- High early strength
- Fluid, self-leveling consistency
- Excellent adhesion to steel
- Good impact resistance
- Chemically resistant
- Convenient packaging

### USES

- Anchoring machines, baseplates and other equipment
- Repair of spalled and cracked concrete
- Installation of bolts, anchors and dowels
- Dynamic loads
- Skid resistant surfaces
- Operating temperatures up to 150°F (65°C)

### PACKAGING AND YIELD

Five Star Fluid Epoxy is a two component system consisting of a resin/aggregate preblend and hardener packaged separately inside a pail and is available in a unit yielding approximately 0.20 cubic feet (5.7 liters) of hardened material.

### SHELF LIFE

Two years in original unopened packaging when stored in dry conditions; high relative humidity will reduce shelf life.

TYPICAL PROPERTIES AT 70°F (21°C)		
Compressive Strength, ASTM C 579 A*	Compressive Strength	Compressive Secant Modulus
6 Hours	11,000 psi (75.8 MPa)	3.5 x 10 <sup>5</sup> psi (2.4 x 10 <sup>3</sup> MPa)
1 Day	13,000 psi (89.6 MPa)	4.3 x 10 <sup>5</sup> psi (2.9 x 10 <sup>3</sup> MPa)
7 Days	14,000 psi (96.5 MPa)	4.8 x 10 <sup>5</sup> psi (3.3 x 10 <sup>3</sup> MPa)
Creep, ASTM C 1181, 1 Year	1.8 x 10 <sup>-3</sup> in/in (mm/mm) at 140°F (60°C), 600 psi (4.1 MPa)	
Tensile Strength, ASTM C 307	2400 psi (16.5 MPa)	
Flexural Strength, ASTM C 580	6800 psi (46.9 MPa)	
Flexural Secant Modulus, ASTM C 580	1.0 x 10 <sup>6</sup> psi (6.9 x 10 <sup>3</sup> MPa)	
Coefficient of Expansion, ASTM C 531	32 x 10 <sup>-6</sup> in/in/°F (57.6 x 10 <sup>-6</sup> mm/mm/°C)	
Bond to Concrete, ASTM C 882	Concrete Failure	
Working Time at 70°F (21°C)	30 minutes	

\* Rate of loading 0.125 inches per minute. The data shown above reflect typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result. Test methods are modified where applicable.

## PLACEMENT GUIDELINES

- 1. SURFACE PREPARATION:** All surfaces to be in contact with Five Star® Fluid Epoxy shall be free of oil, grease, laitance and other contaminants. Concrete must be clean, sound, dry and roughened to ensure a good bond. An SSPC-SP6 commercial finish on all metal surfaces will optimize bond development to steel.
- 2. FORMWORK:** Formwork shall be constructed of rigid non-absorbent materials, securely anchored, liquid-tight and strong enough to resist forces developed during grout placement. The clearance between formwork and baseplate shall be sufficient to allow for a headbox. The clearance for remaining sides shall be 1 to 2 inches (25 - 50 mm). Areas where bond is not desired must be treated with paste wax or polyethylene. Isolation joints may be necessary depending on pour dimensions. Contact StonCor for further information.
- 3. MIXING:** For optimum performance, all components should be conditioned to between 70°F and 80°F (21°C and 27°C) prior to use. Use mixing paddle and a slow speed drill for mixing. Pre-mix Component A (resin and aggregate preblend) until uniform color and consistency is observed. Pour all of Component B (hardener) into pail containing resin and aggregate blend and mix until a uniform color is achieved. Use immediately after mixing. Working time is approximately 30 minutes when temperatures are at 70°F (21°C).
- 4. METHODS OF PLACEMENT:** Five Star Fluid Epoxy may be poured in place at a thickness of 1/8 inch (3 mm) to 1 1/2 inches (38 mm). A self-leveling product, Five Star Fluid Epoxy needs little or no finishing.
- 5. POST-PLACEMENT PROCEDURES:** In-service operation may begin immediately after minimum required strength and modulus have been achieved. Where a skid resistant surface is required, broadcast sand on fresh uncured epoxy surface. Sweeping away excess sand after epoxy cures leaves a skid resistant finish.
- 6. CLEAN UP:** All tools and equipment may be cleaned with solvents or water and strong detergent solution or suitable solvent before material hardens. Sand may be used as an abrasive.

**NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY.** For more detailed placement procedures, refer to Design-A-Spec™ installation guidelines or call StonCor at (800) 263.3112.

## CONSIDERATIONS

- Flowability and strength gain are adversely affected by lower temperatures.
- To obtain bond, concrete shall be visibly free of surface moisture.
- For placement temperatures below 50°F (10°C) or above 90°F (32°C) contact StonCor Group at (800) 263.3112.
- For placements greater than 1 1/2 inches (38 mm), or greater than 0.20 cubic feet (5.7 liters) contact StonCor Group at (800) 263.3112.

## CAUTION

Irritant, toxic, strong sensitizer. Contains epoxy resin and amine. This product may cause skin irritation. Do not inhale vapours. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. **PRIOR TO USE, REFER TO MATERIAL SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local sales representative, or call StonCor at (800) 263.3112.

WARRANTY: "FIVE STAR PRODUCTS INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

### Important:

StonCor believes the information contained here to be true and accurate as of the date of publication. StonCor makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

07/09



An RPM Company

95 Sunray Street • Whitby, Ontario • L1N 9C9 • Tel: 800.263.3112 • Fax: 800.786.6329

Vancouver • Calgary • Edmonton • Regina • Saskatoon • Winnipeg • Toronto • Ottawa • Halifax  
Saint John • St. John's • Montreal • Gatineau • Québec • Sherbrooke • Trois-Rivières • Chicoutimi

www.stoncorcpg.ca